



# PATRIOT FOAM & COATINGS


## PATRIOT 400GHY OPEN CELL SPRAY FOAM

PATRIOT 400 is a two-component, water-blown (zero ozone depleting chemical) light-density, open cell spray polyurethane foam (SPF) system that is designed to improve the performance of the building envelope for interior commercial, residential and industrial applications.

Physical Properties							
Core Density	ASTM D1622	0.438 LB/FT3	Tensile Strength	ASTM D1623	4.49 psi		
R-Value @ 1"	ASTM C518	4.01	Air Permeance @ 3.5"	ASTM E2178 @ 75 PA	0.010		
Water Vapor Permeance	ASTM E96	16 perms at 2"	Dimensional Stability	ASTM D2126	<8.9%		
Intertek Certified Clean Air Gold: Conforms to California Department of Public Health (CDPH) Standard Method v1.2: Private Office and School Classroom				CDPH 01350 v1.2: PO, SC, R for VOC emissions and formaldehyde			
Liquid Properties		A SIDE: PMDI Isocyanate		B SIDE: Patriot 400 Classic Resin			
Color	Brown		Amber				
Viscosity (Brookfield cps) @ 77°F	200 ± 30		360 ± 100				
Specific Gravity	1.24		1.07				
Mixing Ratio (volume)	1:1		1:1				
Fire Test Results							
Flammability	ASTM E84 @ 4"		15 Flame Spread   200 Smoke Development				
Large Scale Fire Testing: Ignition Barrier	AC 377 Appendix U		PASS: 6 Wet Mils DC 315				
Large Scale Fire Testing: Thermal Barrier	NFPA 286*		PASS: 18 Wet Mils DC 315   14 Wet Mils No-Burn				
Alternative Unvented Attic Assembly*: End Use Configuration Testing	Conforming to IBC Section 1202.3 or IRC Section R806.5		Approved for certain attics without a prescriptive ignition barrier or intumescent coating				
NFPA 259	1,796 Btu/ft <sup>2</sup> @ 3.5"		NFPA 285		PASS		
Reactivity Profile							
Cream Time	1-2 seconds	Gel Time	3-4 seconds	Tack Free	6-7 seconds	End of Rise	6-7 seconds

- See Intertek CCRR-0358 for additional instructions or consult with Patriot Foam's Technical Department for details at 850-640-0285

## PROCESSING PARAMETERS



### Pressure (Dynamic)

- 1200-1400 psi while spraying

### Machine Temperature

- A Side: 110°F to 150°F (43°C to 66°C)
- B Side: 110°F to 150°F (43°C to 66°C)

### Hose Heat Temperature

- 115°F to 140°F (46°C to 60°C)

### Substrate Temperature

- Patriot 400: 40°F to 120° F (4°C to 49°C)

### Drum Temperature

- A Side: 75°F to 100°F (24°C to 38°C)
- B Side: 75°F to 100°F (24°C to 38°C)

### MAXIMUM PASS THICKNESS: 6 INCHES

- Optimal temperature and pressure settings are affected by the equipment being used, as well as ambient and substrate temperatures.
- Important: Many factors affect yield, including substrate temperature, substrate type, and pass thickness. Multiple passes will significantly reduce yield. Larger mixing chamber sizes and higher pressure settings will also reduce yield.

## PROCESSING INSTRUCTIONS - READ CAREFULLY

Agitation	Agitation required at high speed for 20-30 minutes prior to spraying. Agitation during application at medium speed. Recommended agitator: Graco collapsing blade Agitator #26C818 or #26C150.
Drum Temperatures & Recirculation	Recirculate as needed to achieve chemical temperatures in the drums of 75°-95°F for both A Side & B Side drums (this is necessary to bring viscosities of A Side & B Side in alignment to prevent off-ratio foam and increase yield). When recirculating, set the primary heater for A Side to 100°F and B Side to 130°F. Use laser thermometer or inlet temperature gauge to measure drum temperature (A Side drum should NEVER be warmer than B Side drum).
Substrate Condition	Substrate must be clean, dry, and moisture content <19%. Substrate temperature should be >5°F above dew point. When substrate temperature is below 45°F, pre-heat building. When heating concrete or metal substrate with portable heaters, only heat to 50°F, otherwise condensation may form. Never use portable propane heaters.
Spray Technique	Spray side-to-side approximately 18" from surface. The farther away you spray, the colder the chemical will be when it reaches the substrate, increasing the potential for voids. Reverse picture frame technique is also suggested if desired.
High Humidity	When the dew point is greater than 65°F, reduce the A Side temperature by 5°F +/- to reduce ISO reactivity/blow backs.
Contamination	B Side is sensitive to contamination from other products. Never combine this product with any other product and never combine open cell with closed cell products. Transfer pumps must be properly cleaned between product. Recirculating lines must be properly flushed before recirculating.
Max   Min Pass Thickness	Max practical pass thickness is 6-8" before resulting in splash-back. Min recommended pass thickness is 3", except when a flash coat is required. As a general rule of thumb, the hose temperature is the most important setting and should be set first. The A Side is set 2-5°F higher than the hose. The B Side is set 3°-10°F higher than the A Side depending on humidity levels. If ambient conditions are hot and dry, all temperatures may be set the same. At higher elevations, A Side & B Side temperatures may have to be set the same as the hose.
Proper Temperature Settings	
High Altitude	
Heated Hose	The hose temperature is the most important setting and should be set first to desired final chemical temperature at gun. Hose temperature should rarely be adjusted. Primary heaters should be increased if chemical is too cold. A poorly insulated hose may compromise adequate heating and drastically change required temperature settings. Never increase hose temperature above 145°F - you can burn the hose.

## PROCESSING INSTRUCTIONS (CONTINUED)

<b>Maximizing Yield   Dialing-In Temps</b>	Dozens of factors affect yield, but properly dialing in temperatures has the biggest impact. For open cell, start temperatures hot enough that the foam shrinks slightly from the studs, then lower temperatures 3°F at a time until shrinkage stops; this is the yield sweet spot.
<b>Pressure Settings</b>	Higher fluid pressure settings create more mist and require greater distance from the cavity, resulting in more overspray. Higher pressure will generally lower yield. As a rule of thumb, you should practice spraying as close to 1000 psi as practical.

## TROUBLESHOOTING GUIDE

<b>Poor Adhesion Between Layers or "Fish Eye" Cells</b>	If the foam does not adhere to itself and/or contains large random cells that appear like "fish eyes," the cause may be trapped steam between layers. Allow the first layer to cool before applying second layer.
<b>Pulls Away from Studs or Deflates</b>	If foam pulls away or "shrinks" from studs within a few seconds, then it is too hot. Lower primary heaters and hose temperatures by 3°F. Spray out chemical in hose (approximately 2-3 gallons) until reduced temperature is achieved. If problem does not resolve, lower temperature by another 3°F, and repeat process until resolved. If foam pulls away from studs several minutes after application, then chemical may be contaminated. If foam shows voids behind it or delaminates, there are four possible causes: (1) If stringy fibers ("coconut hairs") appear between the substrate and foam, the foam may be too cold. Increase all heaters by 5°F and spray out chemical in hose until new increased temperatures are achieved. Repeat process until problem is resolved; (2) If the foam is not stringy but has a crusty skin, it may be too hot. Decrease temperatures by 5°F; (3) Substrate moisture content may be too high. Try lowering A Side by 5°F and call Tech Support; (4) Substrate may be too cold - try a 1/4" - 1/2" initial flash coat.
<b>Voids Behind Foam or Delamination</b>	
<b>Voids &amp; Shrinking</b>	If foam creates voids and shrinks from studs at the same time, then increase B Side drum temperature only to 100°F. Machine ΔT may be too low. If the foam has consistently large cell structure resembling a beehive, then the foam may be too cold. Increase all heaters by at least 10°-15°F. If problem persists, chemical may be contaminated.
<b>Beehive Cell Structure</b>	
<b>Color</b>	If the foam appears yellowish or shows marbling, it is likely too cold. Primary heaters should be increased 3°-5°F. Foam should appear white.
<b>Crunchy or Gummy</b>	If foam is crunchy and amber in color, then foam may be ISO rich and off-ratio. If "gummy" consistency, then foam may be resin rich. Check equipment.
<b>Poor Yield</b>	Many factors affect yield, including low substrate temp, metal or concrete substrates, thin layers, multiple layers, larger mixing chamber sizes, higher pressure settings, and off-ratio foam. If temperatures are dialed-in too cold, then lack of heat will generate poor chemical reactivity & poor yield (See <i>Drum Temperatures &amp; Maximizing Yield</i> under <b>Processing Instructions</b> ). B Side may not be thoroughly mixed and may require agitation. Check chemical expiration.
<b>Important</b>	Regardless of proportioner heating capacity, never spray from cold drum chemical. Powerful primary heaters may scorch B Side resin. Follow <i>Drum Temperatures &amp; Recirculation</i> procedures under <b>Processing Instructions</b> .

## Cautions and Recommendations

Patriot 400 is designed for installation in most standard construction configurations using common materials such as concrete, metal, and wood products. Foam plastic installed in walls or ceilings may present a fire hazard unless protected by an approved, fire-resistant thermal barrier with a finish rating of not less than 15 minutes as required by building codes. Rim joists/header areas in accordance with the IRC® and IBC® may not require additional protection. Foam plastic must also be protected against ignition by code-approved materials in attics and crawl spaces, or as code approved alternatives apply.

As with all SPF systems, improper application techniques should be avoided and any defective product replaced with properly installed materials. Examples of improper application techniques include, but are not limited to: excessive application thickness, off-ratio material and spraying into or under rising liquid foam. Additionally, off-ratio materials can result in offensive odors that may not dissipate. It is the responsibility of the applicator to understand how their equipment works.

## Jobsite Warnings

Applicators should ensure the safety of the jobsite and construction personnel. SPF installation is combustible and appropriate signs shall be posted warning that all "hot work" such as welding, soldering, and cutting with torches should not take place until a thermal barrier or approved equivalent is installed over any exposed polyurethane foam.

Contractors should communicate with other trades working in proximity to the spray application area. Appropriate warning signs should be posted at each entryway, clearly indicating that spray foam activity is in progress and that proper respiratory protection is required for entry. Non-SPF personnel and occupants should be vacated from the building during the application of SPF. Proper ventilation during spraying and afterwards at minimum 10 air changes per hour. **Re-Entry:** Ventilate for 2 hours before personal protective equipment is no longer required for trades and inspectors. **Re-Occupancy:** After 24 hours of continuous ventilation, building may be re-occupied.

## Health and Safety Information

Before working with this product, you must read and become familiar with available information, including the Safety Data Sheet (SDS), regarding the risks, proper use and safe handling. All contractors and applicators must use appropriate respiratory, skin and eye Personal Protective Equipment (PPE) when handling and processing spray foam systems.

Refer to the Center for the Polyurethanes Industries (CPI): *Guidance for Developing a Written Respiratory Protection Program, Guidance on Best Practices for the Installation of Spray Polyurethane Foam, and Spray Foam Product Stewardship Guidance*, available at [www.spraypolyurethane.org](http://www.spraypolyurethane.org) and [www.patriotfoam.com](http://www.patriotfoam.com).

## Shelf Life and Storage

Patriot 400 has a shelf life of approximately six months from the date of manufacture when stored in original, unopened containers at 50°F-80°F. This material should be stored in a secure location and never in direct sunlight. Storage temperatures above the recommended range will shorten shelf life.

## Vapor Retarder

Patriot 400 is intended for indoor applications and is a Class III vapor retarder. It is vapor semi-permeable and will allow for some diffusion of moisture through the insulation. The following considerations are needed:

- (1) An additional vapor retarder may be needed in certain building envelopes in climate zones 5 and higher when not meeting the conditions of IRC Table 402.5.1. Refer to local building codes.
- (2) A vapor retarder also needs to be considered where high interior humidity conditions exist.



**DISCLAIMER:** Please read all information in the general guidelines, Technical Data Sheets, Application Guide and Safety Data Sheets before applying material. Patriot products are for professional use only and preferably applied by professionals who have prior experience with Patriot products or have undergone training in application of Patriot products. Published technical data and instructions are subject to change without notice. Contact your local Patriot representative or visit our website for current technical data and instructions. All guidelines, recommendations, statements, and technical data contained herein are based on information and tests we believe to be reliable and correct, but accuracy and completeness of said tests are not guaranteed and are not to be construed as a warranty, either expressed or implied. It is the user's responsibility to satisfy himself, by his own information and tests, to determine suitability of the product for his own intended use, application and job situation. User assumes all risk and liability resulting from his own use of the product. We do not suggest or guarantee that any hazards listed herein are the only ones that may exist. Neither seller nor manufacturer shall be liable to the buyer or any third party for any injury, loss or damage directly or indirectly resulting from use of, or inability to use, the product. Recommendations or statements, whether verbal or in writing, other than those contained herein shall not be binding upon the manufacturer, unless in writing and signed by a corporate officer or the manufacturer. Technical and application information is provided for establishing a general profile of the material and proper application procedures. Test performance results were obtained in a controlled environment and Patriot makes no claim that these tests or any other tests, accurately represent all environments. Patriot is not responsible for typographical errors.